



New Riverside Ochre

SRC-08-12

Rev. Date: 06/25/2014

Approved By: _____

RAD BAN™

TYPICAL ANALYSIS

BaSO ₄	95%
Fe ₂ O ₃	3%
SiO ₂	2%
Specific Gravity	min. 4.3

COARSE RAD BAN™ GRADATION (% PASSING)

1½"	100%
1"	95 – 100%
½"	50 – 80%
#4 Mesh	2 – 30%

FINE RAD BAN™ GRADATION (% PASSING)

¾"	100%
#4 Mesh	95 – 100%
8	60 – 85%
16	40 – 80%
30	25 – 60%
50	5 – 30%
100	5 – 20%

RAD BAN™ MASONRY BLEND GRADATION (% PASSING)

16	90 – 100%
30	55 – 85%
50	30 – 60%
100	5 – 20%

WARRANTY DISCLAIMER

The facts stated and recommended regarding NRO products are based on our own research and the research of others, and are believed to be accurate. NRO products are sold without WARRANTY, expressed or implied, and on the condition that the purchasers conduct their own tests in order to determine the suitability of such for their particular purpose. The user is solely responsible for the use and information regarding NRO products. NRO disclaims any warranty of merchantability or fitness of this product for any particular purpose.

New Riverside Ochre Company, Inc. • 75 Old River Road, SE • P.O. Box 460 • Cartersville, GA 30120
Phone (770) 382-4568 • (800) 248-0176 • Fax (770) 387-1658
www.nrochre.com